

Epigrout LV

Low viscosity epoxy resin crack injection grout

DESCRIPTION

Epigrout LV is a low viscosity epoxy grout based on specially selected epoxy resins and hardeners to produce a highly fluid grout for injection into cracks in masonry and concrete.

ADVANTAGES

- Low viscosity
- High strength
- Easy application
- Excellent adhesion
- Convenient mix ratio

TYPICAL PROPERTIES

Pot Life 20°C		35 minutes
Viscosity @ 20°C		350 Centipoise
Specific Gravity 20°C		1.05
Mix Ratio	Base	Two Volumes
	Hardener	One Volume

APPLICATION INSTRUCTIONS

Preparation

All contacted surfaces must be free of oil, grease or other contamination which may inhibit bond. Any loose concrete should be removed and repaired to provide a solid foundation. Rake out all cracks to allow the grout to penetrate. Oil free compressed air will remove the fine dust which blocks small cracks.

Mixing

Epigrout LV is suitable for mixing using a drill and suitable paddle, or metering pump where a large quantity is required. Mix for 3 to 5 minutes to ensure thorough mixing. Only mix that quantity of material that can be used within the setting time.

Where the Epigrout LV is mixed in the 300m1 kit, add all the hardener to the base component bottle, reseal, and shake vigorously to mix. Do not attempt to rework or retemper any partially set product.

Avoid waste by using all the kit within 15 minutes of mixing. NB: Liquid epoxy grouts will exotherm and set prematurely if not used immediately.

Application

Application by Gravity

This method is only suitable for repair to floor slabs or other horizontal surfaces. Use Silicone sealant or other easily removed material to form a weir either side of the cracks to provide a reservoir for the grout. Place the mixed Epigrout LV in the reservoir and maintain the level of liquid by topping up the grout. When the crack is saturated, allow the grout to gel before removing the excess and weir with a scraper. NB: Hardened grout can only be removed by grinding.

Application by Pump

Prepare the cracks to be grouted by bonding the injection ports over the crack using XLSet 621. Spread a thin layer of XLSet 621 over the cracks to be grouted and allow to set overnight. Set the mix ratio of the pump to 2 to 1 by volume. Pour the individual components of the Epigrout LV into the respective tanks for the base and hardener. NB: Ensure the tanks are clearly identified to avoid mixing base and hardener together. Commence grouting by pumping from the lowest placed injection port. Continue pumping until the Epigrout LV appears at the next port.

MARKETING SERVICES

THOMSON WHITE AUST P/L
250 Princes Hwy Dandenong Vic 3175
Tel: (03) 9791 8211
Fax: (03) 9791 8644
Email: ask@thomsonwhite.com.au

EPIGROUT LV

Application (cont)

Seal off the first port and continue pumping from the second port. Ensure that the operation is completed in one continuous pour. Allow the grout to harden before grinding off the injection ports and epoxy.

Curing

EpigROUT LV is suitable for grinding off after 24 hours. Allow 7 days for full cure.

CLEAN UP

Clean all equipment with immediately after use.

ESTIMATING

Packaging

EpigROUT LV is supplied in ready to use 300 ml kits, as well as 1.5, 6, and 30 litre kits.

STORAGE

EpigROUT LV is an epoxy based product which must be stored in the original unopened containers.

PRECAUTIONS

Where temperatures less than 5°C or greater than 35°C are encountered, contact our Technical Staff for specific advice.

EpigROUT LV is non toxic, but it is alkaline in nature. Any contact with eyes or skin should be washed off with soap and clean water, NOT solvent. Protective gloves, goggles and clothing should be worn. Repeated contact with epoxy resins and hardeners can cause sensitization in some people handling this type of product. Where this occurs seek medical advice before continuing use.

NOTE

Material safety data sheets for these and all AFTEK products are available on request. Read the MSDS and product label carefully before using.

All reasonable care is taken in the compilation of this data sheet. All recommendations regarding use are made without guarantee as the conditions of use are beyond the control of the manufacturer.

ALLIED PRODUCTS

Aftek manufactures a broad range of construction products including:

Grouts

Coatings

Admixtures

Adhesives

Sealants

Floor Toppings

Floor Levelling Compounds

Concrete Repair